

Machining Guide

- Machinability
 - Chip Control
- Speeds and Feeds
- Quality

Machinability

Dura-Bar is an engineered iron that offers machining advantages over carbon and alloy steel as well as other continuous cast iron bars.

By using Dura-Bar you will be able to reduce overall costs by decreasing your cycle time, thereby increasing your parts per hour.

You will see significant improvement over steel in:

- Machinability
- Tool Wear
- Chip Control
- Surface Finish
- Minimal Deburring



The Dura-Bar advantage is the ability to machine at high speeds with little increase in the wear rate of the insert. The difference between Dura-Bar ductile iron and carbon steel is the ability to machine at speeds in excess of 800 sfm without a dramatic decrease in insert life.



Machinability rating of Dura-Bar vs. carbon steel. Ratings based on percentage of tool life at 450 sfm using high speed steel tooling compared to 1212 steel at 100%.

Chip Control



Dura-Bar ductile iron chips: consistent and controllable chip formation



Dura-Bar gray iron chips: fine, compact, consistent and controllable chip formation



Steel chips: typical stringy, uncontrollable chip formation

Speeds and Feeds

Below are the commonly used speeds* for acceptable tool life, based on an independent machine shop study.

SSDI/65-45-12 Ductile Iron

Machining Operation	Machining Speed (sfm)	Feed (ipr)
Rough Turn (OD & ID)	800 - 1,000	.014028
Finish Turn (OD & ID)	1,200 - 1,500	.004020
Drilling/Milling (indexable)	475 - 825	.004012
Drilling/Milling (solid carbide)	450 - 900	.003012
Grooving (OD & ID)	400 - 800	.002007

80-55-06 Ductile Iron

Machining Operation	Machining Speed (sfm)	Feed (ipr)
Rough Turn (OD & ID)	600 - 800	.008024
Finish Turn (OD & ID)	900 - 1,200	.004020
Drilling/Milling (indexable)	410 - 650	.004015
Drilling/Milling (solid carbide)	350 - 600	.003012
Grooving (OD & ID)	400 - 600	.002007

100-70-03 Ductile Iron

Machining Operation	Machining Speed (sfm)	Feed (ipr)
Rough Turn (OD & ID)	450 - 700	.008022
Finish Turn (OD & ID)	700 - 850	.006010
Drilling/Milling (indexable)	400 - 600	.004012
Drilling/Milling (solid carbide)	250 - 350	.003012
Grooving (OD & ID)	300 - 500	.002007

G2P and G2 Gray Iron

Machining Operation	Machining Speed (sfm)	Feed (ipr)
Rough Turn (OD & ID)	800 - 1,100	.014028
Finish Turn (OD & ID)	1,000 - 1,500	.004020
Drilling/Milling (indexable)	410 - 700	.004015
Drilling/Milling (solid carbide)	350 - 700	.003012
Grooving (OD & ID)	400 - 650	.002007

Typical Depth of Cut: Rough Turn = .100" - .175" and Finish Turn = .010" - .050"

* Note: The recommended speeds listed above should be used on Dura-Bar cast iron only. These grades are specially produced to maximize speeds and feeds. Carbides, inclusions and other processing variables that have not been properly controlled will not allow all cast iron grades to be machined at the above speeds, and serious damage may occur to machine tools.

Quick Tips:

Inserts: For best results, use standard coated carbide insert grades, developed specifically for cast iron.

Chip Breakers: You will get good results with or without a chip breaker. A complex chip breaker design is not required due to the free-machining properties of Dura-Bar.

Coolant: Use water soluble or semi-synthetic coolant at a 4-6% concentration level.

Surface Finishes: In drilling, milling and turning Dura-Bar ductile iron, excellent surface finishes, similar to 1144 steel, can be achieved.

Faster Speeds:

Due to its dense fine-grained microstructure, Dura-Bar is clean and consistent, allowing for faster machining speeds than sand castings.



Quality

How Ductile Iron is Superior to Steel...

- Tool life up to 2 times longer at 800 SFM
- Comparable mechanical strengths, even after heat treat
- It is 9% lighter weight and reduces vibration by 70%
- Superior wear resistance

A Commitment to Quality

Dura-Bar is an ISO-9001 Registered company comitted to quality. We maintain our position as industry leader by producing the most consistently reliable, highest quality products.

Dura-Bar is pleased to offer its Zero Defect Guarantee against foundry defects. This Guarantee provides for the replacement of defective material and reimbursement of your cost of machining.



Please contact us for details about the guarantee, or visit our website at www.dura-bar.com.

What Graphite Does...

- Enhances machining by acting as a chip breaker
- Increases tool life by dissipating heat

R

П

- Reduces friction on the insert
- Improves wear performance in the application

Quick Formulas:

RPM = (SFM x 3.82) / Diameter of Cut SFM = (RPM x Diameter of Cut) / 3.82

61 West Mountain St Worcester, MA 01606

CONTACT INFORMATION Tel: 508.853.3630 Fax: 508.853.7485 Toll Free: 1.800.325.3245

www.petersonsteel.com sales@petersonsteel.com